

Formula 962

10/9/97

DESCRIPTION

Formula 962 is an outstanding general-purpose hot melt adhesive, specifically designed for woodworking applications. Its medium viscosity allows high delivery rates and provides medium working time (30-40 seconds).*

NON-TOXIC

The components in Formula 962 have been analyzed by a qualified toxicologist and this product is certified to be non-toxic. Additionally, Formula 962 meets FDA CFR 175.105 adhesive requirements for indirect contact with food.

TYPICAL USES

Furniture - softwood and hardwood, particle board, fir, toys, games, novelty assembly, luggage assembly, packaging, foundry sand cores.


PRODUCT SPECIFICATIONS

Softening point	208°F (98°C)
Viscosity @ 350°F (176°C), centipoise	6,000
Specific gravity	0.98
Shear tensile strength on pine, psi	625
Adhesive tensile on pine, psi	298
Adhesive tensile on steel, psi	464
Hardness @ 72°F (25°C)	84
Heat resistance	130°F (54°C)
Open time (approx.), seconds	30-40

Test Method

ASTM E28-67
Brookfield Thermosel
ASTM 1475
ASTM D-1002
ASTM D-1344-78
ASTM D-1344-78
Shore "A"
AdTech
AdTech

VISCOSITY PROFILE



APPLICATION

For optimum performance, Formula 962 should be applied in one of AdTech's reliable hand held hot melt applicators.

* In typical use applications of 1/8" bead on fir.

IMPORTANT NOTICE: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable but the accuracy of completeness thereof is not guaranteed, and the user should determine the suitability of the product for the intended use. AdTech disclaims any responsibility for any warranties of merchantability and fitness for purpose, verbal recommendations of its representatives and consequential damages.

Adhesive Technologies, Inc. / 3 Merrill Industrial Drive, Hampton, NH 03842 USA / Tel: 603 926 1616 / Fax: 603 926 1780